



PALCLEAR®

Flat Transparent PVC Sheet




CONSTRUCTION



FABRICATION



SIGN & DISPLAY



Overview

PALCLEAR provides an excellent solution to many indoor applications.

PALCLEAR combines excellent mechanical properties, impact strength, water-clear clarity, excellent resistance to chemicals and fire resistance. It withstands many chemical agents and can be easily formed using various fabrication techniques.

Optional characteristics range from high clarity and anti-glare surface to increased impact resistance.

Main Benefits

- Excellent resistance to chemicals
- High fire rating
- High light transmission
- Water Clear Clarity
- Optional high-impact and UV resistance
- Formable: can be thermoformed, vacuum formed, bent hot or cold, fabricated
- PALCLEAR® Matte: Anti-glare finish on one side to eliminate reflection



Typical Applications

- Transparent advertising
- Indoor signage
- High impact glazing
- Machine guards
- Chemically resistant safety glazing
- Fabrication and forming applications
- Anti-glare glazing and frame covers



www.palram.com

Build On.

Colors

Transparent	Water-Clear, Bronze, Bluish
Translucent	White Opal, White Diffuser

Standard Dimensions

Thickness (mm)	Dimensions (mm)	PALCLEAR®	PALCLEAR® UV	PALCLEAR® HI
1-2	1000x2000			✓
	1220x2440			✓
	1300x2500			✓
	1500x3000			✓
	2000x3050			✓
3-4	1000x2000	✓	✓	
	1220x2440	✓	✓	
	1300x2500	✓	✓	
	1500x3000	✓	✓	
	2000x3050	✓	✓	
5-6	1000x2000	✓	✓	
	1220x2440	✓	✓	
	1300x2500	✓	✓	
8-15	1000x2000	✓		
	1220x2440	✓		
	1300x2500	✓		

*Other dimensions are available, subject to minimum quantity.

PALCLEAR® Product Range

Product	Description
PALCLEAR® Water Clear*	Clear UV stabilized PVC sheet
PALCLEAR® Bluish	Bluish tint
PALCLEAR® UV	UV protected on one side
PALCLEAR® HI	High Impact
PALCLEAR® Embossed	Prismatic embossed finish on one side
PALCLEAR® Matte	Matte finish on one side
PALCLEAR® Diffuser	For indoor light box applications

*Water-Clear is PALCLEAR's standard color. Bluish tint is available upon request.

Flammability

PALCLEAR is self-extinguishing and complies with the most demanding international fire resistance standards in the field of plastics, as indicated in the detailed table herein. The classification is subject to product type, thickness and color.

Standard	Classification*
EN 13501	B, s3, d0
BS 476/7	Class 1
UL 94	V-0

* For more detailed information please contact your Palram distributor.

Typical Physical Properties


Property	Method*	Conditions	Units	Value
Density	D-792		g/cm ³	1.4
Water absorption		24 hr. at 23°C	%	0.03
Heat deflection temperature	D-648	Load: 1.82MPa	°C	62 to 65
Service temperature range			°C	0 to +50
Thermal conductivity	C-177		W/m K	0.15
Coefficient of linear thermal expansion	D-696		cm/cm °C	6.7 x 10 ⁻⁵
Tensile strength at yield	D-638	10 mm/min.	MPa	71
Tensile strength at break	D-638	10 mm/min.	MPa	35
Elongation at yield	D-638	10 mm/min.	%	3
Elongation at break	D-638	10 mm/min.	%	60
Tensile modulus of elasticity	D-638	10 mm/min.	MPa	3,600
Flexural strength	D-790	1.3 mm/min.	MPa	103
Flexural modulus	D-790	1.3 mm/min.	MPa	3,400
Impact behavior - Falling dart	ISO 6603/1 E ₅₀	1.3 mm/min.	J	95
Light transmission	D-1003	3mm clear sheet	%	85

*ASTM except where noted otherwise.

**PALCLEAR becomes brittle below 0°C, although it will not be damaged if no impact occurs.

Impact Resistance

PALCLEAR HI and PALCLEAR offer a wider choice to designers and fabricators for point of sale and general fabricated items, particularly when compared to the impact properties of acrylic and polystyrene sheets.



PALRAM H.Q.

Tel: +972 4 8459900
Fax: +972 4 8444012
palram@palram.com

PALRAM EUROPE LTD.

Tel: +44 1302 380777
Fax: +44 1302 380788
sales.europe@palram.com

PALRAM AMERICAS

Tel: 610 2859918
Fax: 610 2859928
palramamericas@palram.com



61282 - 03.2019

In as much as Palram Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any Palram Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. Palram Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local Palram Industries supplier to ensure that you have obtained the most up to date information.

©1997 Palram Industries Ltd. | PALCLEAR is a registered trademark of Palram Industries Ltd.

